



POWEROIL TOPAZ HN 500

These are severely Hydrotreated Heavy Naphthenic Oils meets the requirement of 21 CFR 178.3620(C).

Sr.No.	Characteristics	Unit	Test Method	Typical Data	
				Min.	Max.
1.	Appearance	-	Visual	Clear & Bright	
2.	Density @ 15° C,	gms/cc	ASTM D 1298	0.890	- 0.910
3.	Color,	Saybolt	ASTM D 156	+10	+ 20
4.	Kinematic Viscosity at 40 °C	cSt	ASTM D 445	95	110
5.	Flash Point, (COC)	° C	ASTM D 92	210	
6.	Pour Point	° C	ASTM D 97		-18
7.	Aniline Point	° C	ASTM D 611	95 – 110	
8.	Carbon Type Analysis				
	Aromatics	%	ASTM D-2140	2.00 (Typ.)	
	Paraffinic	%		53.00 (Typ.)	
	Naphthanic	%		45.00 (Typ.)	

Application: Used in applications of Adhesive, Non-Hygiene products, Tapes & Labeling & TPE'S.

(Version # 0 October, 2014)

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.