



## POWERINK OIL N 20

POWERINK OIL N 20 is manufactured from highly refined and severely hydro treated Naphthenic base oils. They have excellent solvency and drying properties.

Sr. No	Characteristics	Unit	Test Method	Guaranteed Data	
				Min	Max
1	Appearance		Visual	Clear Liquid	
2	Color		ASTM D - 1500		1
3	Density at 29.5 ° C	gm / ml	ASTM D - 1298	0.86	0.90
4	Kinematic Viscosity at 40 ° C at 100 ° C	cSt	ASTM D - 445	18 3	22 4
5	Flash point, COC	° C	ASTM D - 92	160	
6	Pour Point	° C	ASTM D - 97		- 36
7	Aniline Point	° C	ASTM D - 611	70	85
8	Hydrocarbon Type Analysis		ASTM D - 2140		
	Ca	%		10 ( Typical )	
	Cp	%		50 ( Typical )	
	Cn	%		40 ( Typical )	
9	Poly Cyclic Aromatics ( PCA )	%	IP 346		3
10	Boiling Range ( IBP min / FBP max )	° C	ASTM Distillation	310	425

Note : Data listed above are typical values. Slight fluctuations in values may be expected on occasions due to Permissible variations in raw material stocks , processing and test procedures.

### APPLICATIONS:

POWERINK OIL N 20 finds its major use in offset type coldest inks for dissolving the resins and as viscosity reducer to suite end application.

( Version # 4 November 21<sup>st</sup> 2012 )

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.