



## POWEROIL TO 10 BS

POWEROIL TO 10 BS is an Uninhibited Transformer Oil meeting BS 148 Class II : 1984 Standard Specification. It also meets the ASTM D 1275 B Test requirement for Corrosive Sulphur.

| Sr No | Characteristics   | Unit                  | Test Method   | Guaranteed Data                               |            |
|-------|---|-----------------------|---|---|------------|
|       |   |                       |   | Min   | Max        |
| 1     | Appearance  |                       | Representative sample of the oil shall be examined in transmitted light under an oil depth of 100 mm at ambient temperature | Clear free from sediment and suspended matter |            |
| 2     | Density at 20 °C  | kg / dm <sup>3</sup>  | BS 4714   |   | 0.895      |
| 3     | Kinematic Viscosity at 40 °C<br>at - 30 °C  | mm <sup>2</sup> / sec | BS 2000 Part 71   |   | 11<br>1800 |
| 4     | Flash Point, PMCC   | °C                    | BS 2000 Part 34   | 130   |            |
| 5     | Pour Point  | °C                    | BS 2000 Part 15   |   | - 45       |
| 6     | Neutralization Value  | mg KOH/ gm            | BS 2000 Part 1  |   | 0.03       |
| 7     | Water Content , Bulk / Drum   | ppm                   | BS 6470   |   | 30 / 40    |
| 8     | Breakdown Voltage<br>As Delivered   | kV                    | BS 5874   | 30  |            |
| 9     | Dielectric Dissipation Factor (Tan δ) at 90 °C & 40 to 62 Hz                      |                       | BS 573  |   | 0.005      |
| 10    | Corrosive Sulphur<br>Copper Strip, 140 °C, 19 Hrs<br>Copper Strip, 150 °C, 48 Hrs |                       | BS 5680 : 1979<br>ASTM D 1275 B   | Non Corrosive<br>Non Corrosive                |            |
| 11    | Antioxidant Additives   | %                     | BS 5984 : 1980  | Not Detectable                                |            |
| 12    | Oxidation Stability<br>at 120 °C, 164 Hrs   |                       | BS 148 : 1984 Appendix A  |   |            |
|       | Total Acidity   | mg KOH /gm            |   |   | 1.5        |
|       | Sludge  | %                     |   |   | 1.0        |
| 13    | Gassing Tendency at 50 Hz<br>after 120 minutes                                    | mm <sup>3</sup> / min | BS 5797 Method A  |   | + 5        |

(Version # 4 1<sup>st</sup> October , 2014)

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.