



## POWEROIL TO 1020 AUX

POWEROIL TO 1020 AUX is an Inhibited Transformer Oil meeting the ASTM D 3487 - 2016 Type II Standard Specification. It also meets the ASTM D 1275 B Test requirement for Corrosive Sulphur.

Sr No	Characteristics	Unit	Test Method	Guaranteed Data	
				Min	Max
1	Visual Examination		ASTM D 1524	Clear and bright	
2	Aniline Point	° C	ASTM D 611	63	
3	Color		ASTM D 1500		0.5
4	Specific Gravity 15 ° C / 15 ° C		ASTM D 1298 / D 4052		0.91
5	Kinematic Viscosity at 100 ° C	mm <sup>2</sup> /s	ASTM D 445		3.0
	at 40 ° C				12.0
	at 0 ° C				76
6	Flash Point, COC	° C	ASTM D 92	145	
7	Pour Point	° C	ASTM D 97		- 40
8	Inter Facial Tension at 25 ° C	mN/m	ASTM D 971	40	
9	Neutralization Number, Total Acid Number	mg KOH/ g	ASTM D 974		0.03
10	Water Content	ppm	ASTM D 1533		35
11	Dielectric breakdown voltage at 60 Hz VDE electrodes , 1 mm gap 2 mm gap	kV	ASTM D 1816	20 35	
12	Dielectric breakdown Voltage, Impulse conditions, negative polarity point	kV	ASTM D 3300	145	
13	Dissipation Factor ( or power factor) at 60 Hz 25 ° C 100 ° C	%	ASTM D 924		0.05 0.30
14	Corrosive Sulphur		ASTM D 1275	Non Corrosive	
15	Oxidation Inhibitor Content	%	ASTM D 2668		0.3
16	Oxidation Stability at 110 ° C, 72 Hrs		ASTM D 2440		
	Total Acid Number	mg KOH /g			0.3
	Sludge	%			0.1
	at 110 ° C , 164 Hrs				
	Total Acid Number	mg KOH /g			0.4
	Sludge	%			0.2
17	Oxidation Stability ( Pressure vessel test )	minutes	ASTM D 2112	195	
18	Gassing Tendency	µ L / min	ASTM D 2300		+ 30
19	Furanic compounds	µg/L	ASTM D 5837		25
20	PCB Content	ppm	ASTM D 4059	Not Detectable	

(Version # 7 June , 2018)

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.