



POWEROIL TO 335 X

POWEROIL TO 335 X is an Inhibited Transformer Oil meeting Bureau of Indian Standards: IS 12463 -1988 Specification.

Sr No	Characteristics	Unit	Test Method	Guaranteed Data	
				Min	Max
1	Appearance		Representative sample of the oil shall be examined in a 100 mm thick layer at 27°C	Oil shall be clear, transparent and free from suspended matter or sediment	
2	Density at 29.5 ° C	g / ml	IS 1448 P 16 - 1997		0.89
3	Kinematic Viscosity at 27 ° C	cSt	IS 1448 P 25 - 1996		27
4	Flash Point, PMCC	° C	IS 1448 P 21- 1970	140	
5	Pour Point	° C	IS 1448 P10 - 1970		- 6
6	Inter Facial Tension	N / m	IS 6104 - 1971	0.04	
7	Neutralization Value a) Total Acidity b) Inorganic Acidity/Alkalinity	mg KOH/ gm	IS 1448 P 2 - 1967		0.03
					NIL
8	Water Content	ppm	IS 13567 - 1992		50
9	Specific Resistance		IS 6103 - 1971		
	a) at 90 ° C	ohm - cm		35 x 10 ¹²	
	b) at 27 ° C	ohm - cm		1500 x 10 ¹²	
10	Breakdown Voltage		IS 6792 - 1972		
	New Unfiltered / After Filtration	kV		30 / 60	
11	Dielectric Dissipation Factor (Tan δ) at 90 ° C		IS 6262 - 1971		0.002
12	Corrosive Sulphur Copper Strip, 140 ° C, 19 Hrs		IS 335 Annexure B	Non-corrosive	
13	Presence of Oxidation Inhibitor	%	IS 13631 - 1982		0.3
14	Oxidation Stability at 100 ° C, 164 Hrs		IS 335 Annexure C		
	a) Total Acidity	mg KOH / gm			0.4
	b) Sludge	%			0.1
15	Ageing characteristics after accelerated ageing (open beaker method with copper catalyst)		IS 12177 – 1987 Method A		
	Specific Resistance at 27 ° C	ohm - cm		2.5 x 10 ¹²	
	(Resistivity) at 90 ° C	ohm - cm		0.2 x 10 ¹²	
	Dielectric Dissipation Factor (Tan δ) at 90 ° C				0.20
	Total Acidity	mg KOH/ gm			0.05
	Total Sludge	%			0.05
16	Oxidation Stability , RBOT	Minutes		195	

(Version # 5 January, 2018)

Disclaimer: APAR makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the products for the application contemplated by the user is solely their responsibility.