

# Aparprene TPV Catalogue



Properties	Unit	Aparprene TPV 060 AB M	Aparprene TPV 065 AB M	Aparprene TPV 075 AB M	Aparprene TPV 275 AN M	Aparprene TPV 090 AB M	Aparprene TPV 040 DB M	Aparprene TPV 050DB M
<b>HARDNESS</b>	SHORE A/D	59 A	66 A	75 A	77 A	88 A	41 D	51 D
<b>DENSITY</b>	gm/cm <sup>3</sup>	0.97	0.96	0.96	0.97	0.96	0.97	0.95
<b>TENSILE MODULUS @ 100</b>	mpa	1.9	2.2	2.8	3.1	5.2	9	12
<b>TENSILE STRENGTH</b>	mpa	5.8	5.5	5.9	6.1	11	15	15
<b>ELONGATION @ BREAK</b>	%	600	530	411	451	608	550	550
<b>TEAR STRENGTH</b>	kn/m	29	28	36	38	55	96	115
<b>COMPRESSION SET 70°C @ 22 Hrs.</b>	%	36	38	41	41	49	55	61
<b>COMPRESSION SET 125°C @ 70 Hrs.</b>	%	58	60	63	63	64	69	80